

SC « Turkmengas»

High-Density Polyethylene Specification (granulated)

TDS(State Turkmenistan Standart Service)-1097-2018

Mark - HP50-25-155

Melt flow rate, (2.16 kg), g/10min	0,18-0,26
Density, kg/m³	949-953
Tensile yield strength, (2 inch/min) , Mpa	22
Tensile elongation at yield, %	700
Heat resistance on Vicka , Mpa	120
Flexural modulus, Mpa	900