

SC « Turkmengas»

High-Density Polyethylene Specification (granulated)

TDS(State Turkmenistan Standart Service)-1097-2018

Mark - T60-475-119

Melt flow rate, (2.16 kg) , g/10min	4 -5,6
Density, kg/m³	959-963
Tensile yield strength, Mpa	28
Notched izod under load, J/m	55
Flexural modulus (1 mm/min), Mpa	1250
Heat resisitance on Vicka	120 °C