

THE CALCINATED PETROLEUM COKE

TŞ 05766698-17-99

№	Description of index	Figure	
		A	B
1	Mass portion of the total moisture, %, not more than	0,5	0,5
2	Ash content, %, not more than	0,7	0,6
3	Mass portion of sulfur, in %, not more than	1,0	0,8
4	Real density, g/ sm ³ ,	2,01-2,06	2,06-2,08
5	Mass portion of coke with the size of pieces more than 6 mm, %, not less than	30,0	30,0
6	Mass portion of oiled product	-	0,5

Note:

1. The mass portion of the total moisture is not to rejection indicators at shipment in open semicars and serves for calculation with the consumer.
2. The position № 6 is not rejection. Its share exceeding the established norm is not subject to payment.