

SC « Turkmengas»

Polypropylene Specification

TDS(State Turkmenistan Standart Service)-1098-2018

Mark – LH5072-03.O

Melt flow rate, (230°C / 2.16g), g/10 min	3,0-4,0
Density, kg/sm³	0.90-0,91
Tensile yield strength, at 50 mm/min, MPa	33
Tensile elongation at yield, at 50 mm/min, %	7,6
Flexural modulus (1% secant), at 1.3 mm/min, MPa	1275
Notched Izod impact strength, at 23°C, J/m	30