

SC « Turkmengas»

Polypropylene Specification

TDS(State Turkmenistan Standart Service)-1098-2018

Mark - L R7175-35.P

Melt flow rate, (230°C / 2.16g) g/10 min	30,0-40,0
Density, kg/sm³	0.885-0,905
Tensile yield strength, at 50 mm/min, MPa	25
Tensile elongation at yield, at 50 mm/min, %	7,6
Flexural modulus (1% secant), at 1.4 mm/min, MPa	935
Notched Izod impact strength, at 23°C, J/m	29